

:: Multi Silver Light

polyester multifunctional putty

CHARACTERISTICS

Multi Silver Light is a universally adhesive filling and fine putty

- Extremely easy to work
- Layer to any thickness
- Adhesion to galvanised steel sheeting
- Adhesion to aluminium and steel surfaces
- Superlight sanding properties

APPLICATION

For filling in deep uneven areas and dents on motor vehicle bodywork in the area of cars, lorries, buses and railway vehicles.

PRODUCT DATA

MATERIAL DATA:

- **Delivery viscosity at 20°C:** as a paste
- **VOC content:** 2004/42/EG-II;2b(250) < 250g/l
- **Shade:** Silver

HANDLING

BASE:

The base must be clean, dry and grease-free. Good adhesion is achieved on all roughly sanded bases such as e.g. woods, metals (also galvanised) and polyester laminates (not on thermoplastic acrylic systems).

DOSING:

Addition of 2-3 % by weight hardener paste.

Overdosing of the hardener paste is to be avoided. Bleeding-through and colour changes in the finishing coat might be the result.

POT LIFE:

At +20°C room temperature, 4-5 minutes.

REACTION TEMPERATURE:

At least +5°C.

APPLICATION:

Spread on with a spatula

DRYING TIME:

Air drying at + 20°C room temperature, 20 - 30 minutes.

SANDING CHARACTERISTICS:

Following drying times given.

As filling putty

First sanding - dry with P80 - P120

Re-sanding - dry with P120 - 240

As fine putty

First sanding - dry with P120 - P180

Re-sanding - dry with P180 - P240

REWORKING:

The Multi Silver Light putty can be worked over with the following CS products:

- Elastic weiss or Elastic beige and Spray



03/2021

STORAGE:

Ca. 6 - 8 months at 18 - 20° C in closed original container

SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for applying and using our products, are based on our current knowledge and experience when applied under normal conditions. In practice, the materials, surfaces or site conditions are so different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, except we are charged with intent or gross negligence. In this case the user is obliged to prove that he has informed us about all points required for a proper and promising judgement in writing, in time and completely. Patent rights of any third party are to be observed. Furthermore, our general sales and delivery Terms and Conditions and the latest Technical Data Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the specifications of the Employers Liability Insurance Association for the chemical industry.