

Multi Light

polyester multifunctional putty

V06
05/2024

Description

- Multifunctional polyester putty
- Ultra lightweight putty

Area of application

- For filling small to medium-sized imperfections, dents and scratches

Benefits

- Multi adhesion

Product Data

Material data

Viscosity at 20°C: as a paste
 VOC-content: 2004/42/IIIB (b) (250) < 250g/
 Colour: beige

Handling

Surface:

- The substrate must be clean, dry and free of grease.
- Good adhesive properties on all roughly sanded bases.

Dosing

- No more than 2-3% (by weight) of BPO hardener paste should be added to 100 parts of polyester filler.
- Excessive amounts of BPO hardener paste can cause a colour change of the topcoat.

Pot-life:

- At +20°C room temperature, 3-4 minutes

Reaction temperature:

- At least +5°C.

Application:

- Spread on with a spatula

Hardening time:

- Air drying at + 20°C room temperature, 20 - 30 minutes.

Sanding:

- After the specified drying time.

Reworking:

- The Multi Light putty can be worked over with the following CS products - Elastic weiss or Elastic beige and Spray

Storage:

- ca. 6 - 8 months at 18 - 20° C in closed original container

Information about adhesion

Steel	Aluminium	galvanized tin	GRP	Plastic	2K Polyester putty	Wood
√	√	√	√	X	√	√

Multi Light

polyester multifunctional putty

V06
05/2024



Notes

Allow the product to reach the recommended application temperature naturally (avoid rapid heating/ cooling). It is not recommended to apply the product at a temperature below 18 °C.

Low application temperature changes the coating's properties and may impair the visual



SAFETY ISSUES

The before mentioned technical data and information, especially the recommendations for

applying and using our products, are based on our current knowledge and experience when

applied under normal conditions. In practice, the materials, surfaces or site conditions are so

different that no warranty regarding the working results or liability, arising out of any relationship, can be inferred neither from this information nor from a verbal consultation, expect we are

charged with intent or gross negligence. In this case the user is obliged to prove that he has

informed us about all points required for a proper and promising judgement in writing, in time

and completely. Patent rights of any third party are to be observed.

Furthermore, our general sales and delivery terms and conditions and the latest Technical Data

Sheet, which should be demanded, apply.

Directions for handling and waste disposal are in our Material Safety Data Sheet and the

specifications of the Employers Liability Insurance Association for the chemical industry.